

Jampilen EP440L

Heterophasic Copolymer



Description:

"Jampilen EP440L" is a medium flow heterophasic polypropylene copolymer with improved balance of mechanical properties. The product features high stiffness and outstanding impact strength at low temperatures and is specifically designed for injection molding applications. In comparison with conventional copolymers with the same MFR and same rigidity, "Jampilen EP440L", exhibits 35% higher toughness.

"Jampilen EP440L" is suitable for a wide range of applications in the packaging, automotive and consumer goods industries. Typical applications include luggage, paint pails, buckets, containers, crates, batteries and large toys.

Processing Method:

Injection molding

Features:

High impact strength
High stiffness
Heterophasic copolymer

Typical Applications:

Packaging, automotive and consumer goods industries
Luggage, paint pails, buckets
Containers, crates, batteries and toys

Approval:

Food

TYPICAL PROPERTIES	VALUE	UNIT	METHOD
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	6	g/10min	ASTM D1238
Density	0.9	g/cm ³	ASTM D1505
Mechanical			
Flexural Modulus	1200	MPa	ASTM D790
Tensile Strength at Yield	23	MPa	ASTM D638
Tensile Elongation at Yield	5	%	ASTM D638
Izod Impact Strength (notched) at 23 °C	> 500	J/m	ASTM D256
Izod Impact Strength (notched) at -20 °C	> 60	J/m	ASTM D256
Thermal			
Vicat softening point (B 120 °C/h, 10N)	145	°C	ASTM D1525
H.D.T. (0.46 MPa)	87	°C	ASTM D648
Accelerated oven ageing in air at 150 °C	360	Hours	ASTM D3012

No. 5, North- Shajarian St., Eyvanak Blvd., Farahzadi Blvd., Shahrak-e-Qods., Tehran, 1467715171, Iran.
Tel: +9821-84286, Fax: +982188563100
Email: info@jppc.ir
www.jppc.ir

This data and information is considered to be correct and offered in good faith as a guide. But we do not warrant or otherwise guarantee the merchantability, fitness for a particular purpose or suitability of this information, products or processes described.