

# Jampilen HP525J

## Homopolymer



### Description:

"Jampilen HP525J" is a medium flow homopolymer with bimodal molecular weight distribution and good clarity intended for BOPP films. The product is suitable for metallizable film, both as monolayer and in coextruded structures. It contains a standard processing stabilization but does not contain any slip, antiblocking agents and is calcium stearate free.

"Jampilen HP525J" offers good optical properties, easy processing and very stable film profile. Typical applications are BOPP packaging films and Solid Phase Thermoforming sheets.

"Jampilen HP525J" is suitable for food contact.

### Processing Method:

BOPP Film  
Thermoforming

### Features:

Medium Flow  
Good processability  
Good transparency and gloss  
Homopolymer

### Typical Applications:

High quality packaging film for food  
Lamination to other films  
Metallizable film  
Medical packaging  
Thermoformed food containers

### Approval:

Food

TYPICAL PROPERTIES	VALUE	UNIT	METHOD
<b>Physical</b>			
Melt Flow Rate (230 °C, 2.16 kg)	3	g/10min	ASTM D1238
Density	0.9	g/cm <sup>3</sup>	ASTM D1505
<b>Mechanical</b>			
Flexural Modulus	1300	MPa	ASTM D790
Tensile Strength at Yield	32	MPa	ASTM D638
Tensile Elongation at Yield	9	%	ASTM D638
Izod Impact Strength (notched) at 23 °C	> 30	J/m	ASTM D256
<b>Thermal</b>			
Vicat softening point (B 120 °C/h, 10N)	152	°C	ASTM D1525
H.D.T. (0.46 MPa)	90	°C	ASTM D648
Accelerated oven ageing in air at 150 °C	360	Hours	ASTM D3012
<b>Optical</b>			
Haze (1mm)	0.5	%	ASTM D1003

No. 5, North- Shajarian St., Eyvanak Blvd., Farahzadi Blvd., Shahrak-e-Qods., Tehran, 1467715171, Iran.

Tel: +9821-84286, Fax: +982188563100

Email: [info@jppc.ir](mailto:info@jppc.ir)

[www.jppc.ir](http://www.jppc.ir)

This data and information is considered to be correct and offered in good faith as a guide. But we do not warrant or otherwise guarantee the merchantability, fitness for a particular purpose or suitability of this information, products or processes described.