Jampilen HP545J

Homopolymer



Description:

"Jampilen HP545J" is a medium flow homopolymer with bimodal molecular weight distribution and very good clarity with optical brightener that intended for BOPP films. The product is suitable for metallizable film, both as monolayer and in coextruded structures. It contains a standard processing stabilization but does not contain any slip, antiblocking agents and is calcium stearate free.

"Jampilen HP545J" offers very good optical properties, easy processing and very stable film profile. Typical applications are BOPP packaging films and Solid Phase Thermoforming sheets.

"Jampilen HP545J" is suitable for food contact.

Processing Method:

BOPP Film

Thermoforming

Features:

Medium Flow

Good processability

Very good transparency and gloss

Homopolymer

Typical Applications:

High quality packaging film for food

Lamination to other films

Metallizable film Medical packaging

Thermoformed food containers

Approval:

Food

| TYPICAL PROPERTIES | VALUE | UNIT | METHOD |
|---|-------|-------------------|-------------------|
| Physical | | | |
| Melt Flow Rate (230 °C, 2.16 kg) | 3 | g/10min | ASTM D1238 |
| Density | 0.9 | g/cm ³ | ASTM D1505 |
| Mechanical | | | |
| Flexural Modulus | 1400 | MPa | ASTM D790 |
| Tensile Strength at Yield | 29 | MPa | ASTM D638 |
| Tensile Strength at Break | 29 | MPa | ASTM D638 |
| Tensile Elongation at Yield | 7 | % | ASTM D638 |
| Tensile Strain at Break | 150 | % | ASTM D638 |
| Izod Impact Strength (notched) at 23 ⁰ C | > 30 | J/m | ASTM D256 |
| Thermal | | | |
| Vicat softening point (B 120 °C/h,10N) | 152 | $^{0}\mathrm{C}$ | ASTM D1525 |
| H.D.T. (0.46 MPa) | 90 | $^{0}\mathrm{C}$ | ASTM D648 |
| Melting Temperature (⁰ C) | 166 | $^{0}\mathrm{C}$ | ASTM D 4101 |
| Accelerated oven ageing in air at 150 °C | 360 | Hours | ASTM D3012 |
| Optical | | | |
| Haze (20 micron) | 0.5 | % | ASTM D1003 |
| Gloss (45°) | 80 | ••• | ASTM D2457 |
| Yellow Index | -1> | ••• | ASTM D1925 |

No. 5, North-Shajarian St., Evvanak Blvd., Farahzadi Blvd., Shahrak-e-Qods., Tehran, 1467715171, Iran.

Tel: +9821-84286, Fax: +982188563100

Email: info@jppc.ir

This data and information is considered to be correct and offered in good faith as a guide. But we do not warrant or otherwise guarantee the merchantability, fitness for a particular purpose or suitability of this information, products or processes described.